

|                       |                  |
|-----------------------|------------------|
| <b>Prod. Ref.</b>     | PE150-000        |
| <b>Safety cat.</b>    | S3S CI FO SR     |
| <b>Range of sizes</b> | 38 - 48 (5 - 13) |
| <b>Weight (sz. 8)</b> | 540 g            |
| <b>Shape</b>          | A                |
| <b>Width</b>          | 11               |

**Description:** Brown water repellent nubuck shoe, **SANY-DRY**<sup>®</sup> lining, antistatic, anti-shock, slipping resistant, with non metallic **APT PLUS** midsole - type **PS** with Ø 3,0 mm nail.

**Plus:** **LIGHT FOAM** footbed, made of extremely soft and comfortable polyurethane foam. Punched, antistatic, its anatomical shape provides support to the plantar arch; covered with abrasion resistant fabric, it absorbs moisture and keeps always the foot dry; it guarantees excellent comfort and shock absorption.

**Suggested uses:** Construction, maintenance, industries

**Care and maintenance:** Clean after each use and dry off away from direct heat. Avoid contact with aggressive chemicals or extreme temperature. Avoid immersion in sea water, lime water or cement mixed with water



## MATERIALS / ACCESSORIES

|                      |   |
|----------------------|---|
| <b>Complete shoe</b> | <b>Toe cap:</b> <b>ALUMINIUM</b> made, ultra light, impact resistant until 200 J and compression resistant until 1500 kg  |
|                      | <b>Anti perforation midsole:</b> in multi-layers highly tensile fabric, penetration resistant, <b>Zero Perforation</b>  |
|                      | <b>Antistatic shoe:</b> the bottom is fit for the dissipation of electrostatic charges  |
|                      | <b>Cold insulation</b>  |
|                      | <b>Energy absorption system</b>   |
| <b>Upper</b>         | Brown water repellent nubuck thickness 1,6/1,8 mm   |
| <b>Vamp</b>          | Textile, breathable, abrasion resistant, colour black   |
| <b>lining</b>        | Thickness 1,2 mm  |
| <b>Quarter</b>       | <b>SANY-DRY</b> <sup>®</sup> , breathable, abrasion resistant, colour black   |
| <b>lining</b>        | thickness 1,2 mm  |
| <b>Sole</b>          | Antistatic dual-density polyurethane directly injected in the upper:<br>Outsole: black, high density, slipping resistant, abrasion resistant and hydrocarbons resistant,<br>Midsole: black, low density, comfortable and anti-shock |
|                      | Adherence coefficient of the sole (Slip resistance)   |

## SAFETY TECHNICAL SPECIFICATIONS

| Clause EN ISO | Description   | Unit            | Cofra result     | Requirement |
|---------------|---|-----------------|------------------|-------------|
| 20345:2022    |   |                 |                  |             |
| 5.3.2.6       | Shock resistance (clearance after shock)                              | mm              | <b>16</b>        | ≥ 14        |
| 5.3.2.7       | Compression resistance (clearance after compression)                  | mm              | <b>18</b>        | ≥ 14        |
| 6.2.1.1.4     | Penetration resistance<br>( <b>PS</b> requirement with Ø 3,0 mm nail) | N               | <b>1612</b>      | ≥ 1100      |
| 6.2.2.2       | Electric resistance   |                 |                  |             |
|               | - wet   | MΩ              | <b>12,35</b>     | ≥ 0.1       |
|               | - dry   | MΩ              | <b>77</b>        | ≤ 1000      |
| 6.2.3.2       | Cold insulation (temp. decrease after 30' C at -17 °C)                | °C              | <b>5,5</b>       | ≤ 10        |
| 6.2.4         | Shock absorption  | J               | <b>30</b>        | ≥ 20        |
| 5.4.6         | Water vapour permeability   | mg/cmq h        | <b>&gt; 2,7</b>  | ≥ 0,8       |
|               | Permeability coefficient  | mg/cmq          | <b>&gt; 22,2</b> | ≥ 15        |
| 6.3           | Water absorption  |                 | <b>5,6%</b>      | ≤ 30%       |
|               | Water penetration   |                 | <b>0,0 g</b>     | ≤ 0,2 g     |
| 5.5.4         | Water vapour permeability   | mg/cmq h        | <b>&gt; 4,1</b>  | ≥ 2         |
|               | Permeability coefficient  | mg/cmq          | <b>&gt; 47,2</b> | ≥ 20        |
| 5.5.4         | Water vapour permeability   | mg/cmq h        | <b>&gt; 9,4</b>  | ≥ 2         |
|               | Permeability coefficient  | mg/cmq          | <b>&gt; 76,4</b> | ≥ 20        |
| 5.8.4         | Abrasion resistance (lost volume)                                     | mm <sup>3</sup> | <b>48</b>        | ≤ 150       |
| 5.8.5         | Flexing resistance (cut increase)                                     | mm              | <b>0</b>         | ≤ 4         |
| 5.8.7         | Interlayer bond strength  | N/mm            | <b>3,4</b>       | ≥ 3         |
| 6.4.2         | Hydrocarbons resistance (ΔV = volume increase)                        | %               | <b>1,6</b>       | ≤ 12        |
| 5.3.5.2       | ceramic + detergent solution – forepart (contact angle 7°)            |                 | <b>0,41</b>      | ≥ 0,36      |
|               | ceramic + detergent solution – heel (contact angle 7°)                |                 | <b>0,35</b>      | ≥ 0,31      |
| 6.2.10        | SR : ceramic + glycerol – forepart (contact angle 7°)                 |                 | <b>0,37</b>      | ≥ 0,22      |
|               | SR : ceramic + glycerol – heel (contact angle 7°)                     |                 | <b>0,42</b>      | ≥ 0,19      |