



| | |
|-------------------------|------------------|
| Prod. Ref. | 30530-004 |
| Safety cat. | S3 SRC |
| Range of sizes | 36 - 48 (3 - 13) |
| Weight (sz. 8) | 580 g |
| Shape | A |
| Width (3 - 6) | 10 |
| Width (6,5 - 13) | 11 |

Description: Black/blue high tenacity fabric, partly made of ecological yarns, water repellent and leather shoe, **DRYFRESH** 100% polyester fabric lining, antistatic, anti-shock, slipping resistant, non-woven fabric puncture resistant midsole **PEP Plate - Zero Perforation**

Plus: METAL FREE. Polyurethane/TPU sole with 3 self-modelling gel insert with different density in the metatarsal and calcaneal support points, they adapt to the shape of the plantar arch, by absorbing the different percentages of applied loading force. **SALUS** footbed, preformed, holed, made of antistatic expanded polyurethane foam, which can satisfy all different walking needs. The preformed line ensures the proper support throughout the whole working day, in every point of support of the foot. The very low hardness of the material provides a "cushion effect", without affecting the perfect posture of the user during all phases of walking and flexions. Perfumed sole.

Abrasion resistant leather toe cap protection

Suggested uses: Construction, maintenance, industries

Care and maintenance: Clean after each use and dry off away from direct heat. Avoid contact with aggressive chemicals or extreme temperature. Avoid immersion in sea water, lime water or cement mixed with water

MATERIALS / ACCESSORIES

SAFETY TECHNICAL SPECIFICATIONS

| | | Clause EN ISO 20345:2011 | Description | Unit | Cofra result | Requirement |
|----------------------|--|--------------------------------|--|-----------------|-----------------------|-------------|
| Complete shoe | Toe cap: non metallic FIBERGLASS toe cap, impact resistant until 200 J and compression resistant until 1500 kg | 5.3.2.3 | Shock resistance (clearance after shock) | mm | 14,5 | ≥ 14 |
| | | 5.3.2.4 | Compression resistance (clearance after compression) | mm | 19,5 | ≥ 14 |
| | Puncture resistant fabric: conductive, almost entirely recycled, made of special non-woven fibers, penetration resistant, Zero Perforation | 6.2.1 | Penetration resistance | N | To 1100 N | ≥ 1100 |
| | Antistatic shoe: the bottom is fit for the dissipation of electrostatic charges | 6.2.2.2 | Electric resistance | | No Perforation | |
| | | | - wet | MΩ | 263 | ≥ 0.1 |
| | | | - dry | MΩ | 765 | ≤ 1000 |
| | Energy absorption system | 6.2.4 | Shock absorption | J | 27 | ≥ 20 |
| Upper | high tenacity fabric, partly made of ecological yarns, water repellent, colour black/blue | 5.4.6 | Water vapour permeability | mg/cmq h | > 20,7 | ≥ 0,8 |
| | | | Permeability coefficient | mg/cmq | > 186,6 | > 15 |
| | | 6.3.1 | Water absorption | | 15% | ≤ 30% |
| | | | Water penetration | | 0,0 g | ≤ 0,2 g |
| Upper | Black water repellent leather thickness 1,8/2,0 mm | 5.4.6 | Water vapour permeability | mg/cmq h | > 1 | ≥ 0,8 |
| | | | Permeability coefficient | mg/cmq | > 15,2 | > 15 |
| | | 6.3.1 | Water absorption | | 8% | ≤ 30% |
| | | | Water penetration | | 0,0 g | ≤ 0,2 g |
| Vamp | Textile, breathable, abrasion resistant, colour black | 5.5.3 | Water vapour permeability | mg/cmq h | > 6,3 | ≥ 2 |
| | | | Permeability coefficient | mg/cmq | > 51,1 | ≥ 20 |
| lining | Thickness 1,2 mm | 5.5.3 | Water vapour permeability | mg/cmq h | > 9,9 | ≥ 2 |
| | | | Permeability coefficient | mg/cmq | > 80 | ≥ 20 |
| Quarter | DRYFRESH 100% polyester fabric, breathable, abrasion resistant, colour grey thickness 1,2 mm | 5.8.3 | Abrasion resistance (lost volume) | mm ³ | 73 | ≤ 150 |
| | | 5.8.4 | Flexing resistance (cut increase) | mm | 1,5 | ≤ 4 |
| lining | thickness 1,2 mm | 5.8.6 | Interlayer bond strength | N/mm | 4,1 | ≥ 3 |
| | | 6.4.2 | Hydrocarbons resistance (ΔV = volume increase) | % | 3 | ≤ 12 |
| Sole | Antistatic Polyurethane/TPU directly injected in the upper: | 5.3.5 | SRA : ceramic + detergent solution – flat | | 0,37 | ≥ 0,32 |
| | Outsole: Light blue TPU, slipping resistant, abrasion resistant and hydrocarbons resistant. | 5.8.4 | Flexing resistance (cut increase) | mm | 1,5 | ≤ 4 |
| | Midsole: Light grey polyurethane, low density, comfortable and anti-shock. | 5.8.6 | Interlayer bond strength | N/mm | 4,1 | ≥ 3 |
| | Adherence coefficient of the sole | 6.4.2 | Hydrocarbons resistance (ΔV = volume increase) | % | 3 | ≤ 12 |
| | | 5.3.5 | SRA : ceramic + detergent solution – flat | | 0,37 | ≥ 0,32 |

| | | |
|--|-------------|--------|
| SRA : ceramic + detergent solution – heel (contact angle 7°) | 0,29 | ≥ 0,28 |
| SRB : steel + glycerol – flat | 0,19 | ≥ 0,18 |
| SRB : steel + glycerol – heel (contact angle 7°) | 0,15 | ≥ 0,13 |