



<b>Prod. Ref.</b>	31590-001
<b>Safety cat.</b>	S1 P SRC
<b>Range of sizes</b>	39 - 48 (6 - 13)
<b>Weight (sz. 8)</b>	485 g
<b>Shape</b>	A
<b>Width (6)</b>	10,5
<b>Width (6,5 - 13)</b>	11

**Description:** Grey punched suede leather shoe, **SANY-DRY**<sup>®</sup> lining, antistatic, anti-shock, slipping resistant, non-woven fabric puncture resistant midsole **PEP Plate - Zero Perforation**

**Plus: METAL FREE.** Sole made of **XL EXTRALIGHT**<sup>®</sup>: is a **super light, flexible and resistant** expanded material. Low density, excellent physical-mechanical properties, **soft touch**. It does not absorb liquids and external chemical agents (acids/basic agents) and does not allow the proliferation of bacteria; it has an excellent resistance against atmospheric agents especially at low temperatures. Excellent resistance to water, UV rays, chlorine and to salt so that it is resistant to ageing and keeps the colour unchanged over time. **Its lightness** (weight 3 times lower than those materials having the same mechanical properties) **has allowed to produce a safety footwear with very reduced weight (about 420 g).** **The high thickness of the sole maximizes the cushioning effect, by increasing comfort.** **LIGHT FOAM** footbed, made of extremely soft and comfortable polyurethane foam. Punched, antistatic, its anatomical shape provides support to the plantar arch; covered with abrasion resistant fabric, it absorbs moisture and keeps always the foot dry; it guarantees excellent comfort and shock absorption.

**Excellent breathability**

**Suggested uses:** this line is recommended for: logistics, service industry, shipping, light industry, microelectronics industry, food industry. **It is not recommended for heavy industry and construction**

**Care and maintenance:** Clean after each use and dry off away from direct heat. Avoid contact with aggressive chemicals or extreme temperature. Avoid immersion in sea water, lime water or cement mixed with water

### MATERIALS / ACCESSORIES

### SAFETY TECHNICAL SPECIFICATIONS

		Clause EN ISO 20345:2011	Description	Unit	Cofra result	Requirement
<b>Complete shoe</b>	<b>Toe cap:</b> non metallic <b>FIBERGLASS</b> toe cap, impact resistant until 200 J  and compression resistant until 1500 kg	5.3.2.3	Shock resistance (clearance after shock)	mm	<b>14</b>	≥ 14
		5.3.2.4	Compression resistance (clearance after compression)	mm	<b>19</b>	≥ 14
	<b>Puncture resistant fabric:</b> conductive, almost entirely recycled, made of special non-woven fibers, penetration resistant, <b>Zero Perforation</b>	6.2.1	Penetration resistance	N	<b>To 1100 N</b> <b>No Perforation</b>	≥ 1100
	<b>Antistatic shoe:</b> the bottom is fit for the dissipation of electrostatic charges	6.2.2.2	Electric resistance - wet - dry	MΩ MΩ	<b>87</b> <b>289</b>	≥ 0.1 ≤ 1000
<b>Energy absorption system</b>	6.2.4	Shock absorption	J	<b>39</b>	≥ 20	
<b>Upper</b>	Grey suede leather thickness 1,8/2,0 mm	5.4.6	Water vapour permeability Permeability coefficient	mg/cmq h mg/cmq	<b>&gt; 5,1</b> <b>&gt; 42,2</b>	≥ 0,8 > 15
		5.5.3	Water vapour permeability Permeability coefficient	mg/cmq h mg/cmq	<b>&gt; 6,3</b>	≥ 2
<b>&gt; 51,1</b>	≥ 20					
<b>Vamp</b>	Textile, breathable, abrasion resistant, colour black	5.5.3	Water vapour permeability Permeability coefficient	mg/cmq h mg/cmq	<b>&gt; 10,3</b>	≥ 2
<b>lining</b>	Thickness 1,2 mm				<b>&gt; 82,8</b>	≥ 20
<b>Quarter</b>	<b>SANY-DRY</b> <sup>®</sup> , breathable, abrasion resistant, colour fluo orange thickness 1,2 mm	5.8.3	Abrasion resistance (lost volume)	mm <sup>3</sup>	<b>247</b>	≤ 250
						5.8.4
<b>lining</b>	Antistatic EVA directly applied on the upper, colour white, slipping resistant, abrasion resistant and hydrocarbons resistant, comfortable and anti-shock	6.4.2	Hydrocarbons resistance (ΔV = volume increase)	%	<b>7</b>	≤ 12
		5.3.5	SRA : ceramic + detergent solution – flat		<b>0,46</b>	≥ 0,32
<b>Sole</b>	Adherence coefficient of the sole					

SRA : ceramic + detergent solution – heel (contact angle 7°)	<b>0,43</b>	≥ 0,28
SRB : steel + glycerol – flat	<b>0,31</b>	≥ 0,18
SRB : steel + glycerol – heel (contact angle 7°)	<b>0,21</b>	≥ 0,13